



LEXAN* 3412R Resin

SABIC Innovative Plastics Europe - Polycarbonate

Friday, August 01, 2008

General Information

Product Description

LEXAN 3412R is a high viscosity, 20% glass reinforced grade. It offers excellent flame retardancy and is especially designed for applications requiring high rigidity together with high heat.

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber Reinforcement, 20 % Filler by Weight
Additive	• Ignition Resistant
Features	• Flame Retardant • High Rigidity • High Heat Resistance • High Viscosity
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

ASTM and ISO Properties¹

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.35 g/cm ³	1.35 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	0.366 in ³ /10min	6.00 cm ³ /10min	ISO 1133
Molding Shrinkage (Flow)	0.0020 to 0.0050 in/in	0.20 to 0.50 %	ASTM D955
Water Absorption (73 °F (23 °C), Saturation)	0.29 %	0.29 %	ISO 62
Water Absorption 73 °F (23 °C), Equilibrium, 50 % RH	0.12 %	0.12 %	ISO 62

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	870000 psi	6000 MPa	ISO 527-2/1
Tensile Stress (Break)	13100 psi	90.0 MPa	ISO 527-2/5
Tensile Strain (Break)	2.0 %	2.0 %	ISO 527-2/5
Flexural Modulus ²	798000 psi	5500 MPa	ISO 178
Flexural Strength ^{2, 3}	17400 psi	120 MPa	ISO 178
Taber Abrasion Resistance ⁴ (1000 Cycles)	17.0 mg	17.0 mg	ASTM D1044

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			
-22 °F (-30 °C) ⁵	2.38 ft-lb/in ²	5.00 kJ/m ²	ISO 179/1eA
73 °F (23 °C) ⁵	2.86 ft-lb/in ²	6.00 kJ/m ²	ISO 179/1eA
73 °F (23 °C)	4.28 ft-lb/in ²	9.00 kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength ⁵			ISO 179/1eU
-22 °F (-30 °C)	19.0 ft-lb/in ²	40.0 kJ/m ²	
73 °F (23 °C)	19.0 ft-lb/in ²	40.0 kJ/m ²	
Notched Izod Impact Strength ⁶			ISO 180/1A
-22 °F (-30 °C)	2.86 ft-lb/in ²	6.00 kJ/m ²	
73 °F (23 °C)	3.33 ft-lb/in ²	7.00 kJ/m ²	
Unnotched Izod Impact Strength ⁶			ISO 180/1U
-22 °F (-30 °C)	16.7 ft-lb/in ²	35.0 kJ/m ²	
73 °F (23 °C)	16.7 ft-lb/in ²	35.0 kJ/m ²	

Copyright © 2008 - IDES - The Plastics Web ®

The information presented on this data sheet was acquired by IDES from the producer of the material. IDES makes substantial efforts to assure the accuracy of this data. However, IDES assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.

IDES - The Plastics Web ®

800-788-4668 or 307-742-9227 | www.ides.com

LEXAN* 3412R Resin
SABIC Innovative Plastics Europe - Polycarbonate

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness - H 358/30	18100 psi	125 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature ⁷ 66 psi (0.45 MPa), Unannealed	291 °F	144 °C	ISO 75-2/Be
Heat Deflection Temperature ⁷ 264 psi (1.8 MPa), Unannealed	282 °F	139 °C	ISO 75-2/Ae
Vicat Softening Temperature			
--	311 °F	155 °C	ISO 306/A50
--	297 °F	147 °C	ISO 306/B50
--	293 °F	145 °C	ISO 306/B120
CLTE (Flow, 73 to 176 °F (23 to 80 °C))	0.000017 in/in/°F	0.000030 cm/cm/°C	ISO 11359-2
Thermal Conductivity	1.5 Btu·in/hr/ft ² /°F	0.22 W/m/K	ISO 8302
Ball Pressure Test, 257 °F (125 °C)	Pass	Pass	IEC 60695-10-2

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+15 ohm·cm	> 1.0E+15 ohm·cm	IEC 60093
Relative Permittivity			IEC 60250
50 Hz	3.00	3.00	
60 Hz	3.00	3.00	
1E+6 Hz	2.90	2.90	
Dissipation Factor			IEC 60250
50 Hz	0.00100	0.00100	
60 Hz	0.00100	0.00100	
1E+6 Hz	0.01000	0.01000	
Comparative Tracking Index	150 V	150 V	IEC 60112
Electric Strength			IEC 60243-1
0.0315 in (0.800 mm), in Oil	838.20 V/mil	33.00 kV/mm	
0.0394 in (1.00 mm)	508.00 V/mil	20.00 kV/mm	
0.0630 in (1.60 mm), in Oil	635.00 V/mil	25.00 kV/mm	
0.126 in (3.20 mm), in Oil	406.40 V/mil	16.00 kV/mm	

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating - UL (0.0591 in (1.50 mm))	V-0	V-0	UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.0394 in (1.000 mm)	1560 °F	850 °C	
0.0630 in (1.60 mm)	1760 °F	960 °C	
Oxygen Index	37 %	37 %	ISO 4589-2

UL 746	Nominal Value (English)	Nominal Value (SI)	Test Method
RTI Str	266 °F	130 °C	UL 746
RTI Imp	257 °F	125 °C	UL 746
RTI Elec	266 °F	130 °C	UL 746

Processing Information

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	248 °F	120 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.020 %	0.020 %
Hopper Temperature	140 to 176 °F	60.0 to 80.0 °C

Copyright © 2008 - IDES - [The Plastics Web](http://www.plasticsweb.com) ®

The information presented on this data sheet was acquired by IDES from the producer of the material. IDES makes substantial efforts to assure the accuracy of this data. However, IDES assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.

IDES - [The Plastics Web](http://www.plasticsweb.com) ®

800-788-4668 or 307-742-9227 | www.ides.com

LEXAN* 3412R Resin
SABIC Innovative Plastics Europe - Polycarbonate

Injection	Nominal Value (English)	Nominal Value (SI)
Rear Temperature	518 to 572 °F	270 to 300 °C
Middle Temperature	536 to 590 °F	280 to 310 °C
Front Temperature	554 to 608 °F	290 to 320 °C
Nozzle Temperature	536 to 590 °F	280 to 310 °C
Processing (Melt) Temp	554 to 608 °F	290 to 320 °C
Mold Temperature	176 to 248 °F	80.0 to 120 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min (2.0 mm/min)

³ Break

⁴ 1000 g, CS-17 Wheel

⁵ 80*10*3 sp=62mm

⁶ 80*10*3

⁷ 120*10*4 mm, 3.94 in (100 mm)